

## FEATURES & BENEFITS

GLASSIL® Melting Sand is produced from high-purity, whole grain crystalline silica sand. Consistent size distributions and the statistically accurate removal of coarse and fine grains offer glass manufacturers a uniform melt with lower energy requirements, reduced incidence of foaming or formation of bath scum and an optimal mix to fully integrate all batch components.

All GLASSIL grades are processed with rigid adherence to Covia QIP<sup>SM</sup> quality assurance programs. The result is a uniform, chemically pure source of silicon dioxide and a stable alkali contribution for easier, more predictable batch formations. Consistently low levels of iron and other refractive elements offer the advantage of more uniform batch chemistry, for greater control without additions over critical quality parameters like viscosity, color and clarity.

Available throughout North America, GLASSIL consistency and uniformity is ideally suited to standardize incoming raw materials and to optimize batch economics in the production of flat and structural glass, container glass, tableware and decorative wares, fiberglass and silicates.

## PARTICAL SIZE ANALYSIS

*Typical Mean Values. These Do Not Represent A Specification.*

	Mesh Size		GLASSIL® Grade
	ASTM	MICRONS	790
Typical mean % retained on individual sieves	20	850	-
	30	600	-
	40	425	11.6
	50	300	33.4
	70	212	37.1
	100	150	15.0
	140	106	2.8
	200	75	0.1
	PAN	PAN	-

## PHYSICAL PROPERTIES

*Typical Mean Values. These Do Not Represent A Specification.*

GLASSIL® Melting Sand		
Melting Point (°F/°C)	3135/1724	ASTM C-24
Specific Gravity (g/cm <sup>3</sup> )	2.65	ASTM C-128
Moisture Content (%)	<0.1	ASTM C-566
Bulk Density/Loose (lb/ft <sup>3</sup> )	92-95	ASTM C-29
Bulk Density/Compacted (lb/ft <sup>3</sup> )	98-100	ASTM C-29

**CHEMICAL ANALYSIS**

*Typical Mean Values. These Do Not Represent A Specification.*

	Typical Mean Percent by Weight 790
Silicon Dioxide (SiO <sub>2</sub> )	99.53
Iron Oxide (Fe <sub>2</sub> O <sub>3</sub> )	0.058
Aluminum Oxide (Al <sub>2</sub> O <sub>3</sub> )	0.155
Calcium Oxide (CaO)	0.008
Titanium Dioxide (TiO <sub>2</sub> )	0.038
Magnesium Oxide (MgO)	0.009
Potassium Oxide (K <sub>2</sub> O)	0.049
Sodium Oxide (Na <sub>2</sub> O)	0.009
Loss on Ignition (LOI)	0.131

**SHIPPING/ORDERING INFORMATION**

- Shipping Point: Chardon, OH
- Availability: Bulk, IBC, 50 lb Paper Bag  
Truck Only

**CUSTOMER SERVICE**

US & Canada: 1-800-243-9004  
 Fax: 1-800-243-9005  
 Worldwide: 1-203-442-2500  
 Fax: 1-203-972-1378

3 Summit Park Drive, Suite 700, Independence, OH 44131 | CoviaCorp.com

GRADE NUMBERS INDICATE RELATIVE VALUES OR RESULTS. THEY ARE NOT A SPECIFICATION OR WARRANTY OF PERFORMANCE.

Health Hazard Warnings: Prolonged inhalation of dust associated with the materials described in this data sheet can cause delayed lung injury including Silicosis, a progressive, disabling and sometimes fatal lung disease. IARC and NTP have determined that crystalline silica can cause lung cancer in humans. Risk of injury is dependent on the duration and level of exposure. Follow OSHA or other relevant safety and health standards for the form of crystalline silica called Quartz. Current safety data sheet, containing safety information, is available and should be consulted before usage.

Notice: While information contained herein is correct to the best of our knowledge, Covia hereby disclaims any warranties as to the accuracy of the same. Recommendations or suggestions are made without guarantee or representation as to result, since conditions of usage are beyond our control. All materials are sold subject to Covia's standard terms and conditions of sale and the condition that buyer shall make his own tests to determine the suitability of such product for buyer's purpose. No statement contained herein shall be construed as a license to operate under or as a recommendation to infringe any patent.

Silica/Silica Containing

COVIA and GLASSIL® are trademarks of Covia Holdings Corporations and/or its subsidiaries. All rights reserved.