

FEATURES & BENEFITS

GLASSIL® Melting Sand is produced from high-purity, whole grain crystalline silica sand. Consistent size distribution through accurate classification of coarse and fine grains offers glass manufacturers a uniform melt, reduced incidence of foaming and formation of scum, and optimized mixing integration with all batch components.

All GLASSIL grades are processed with rigid adherence to Covia QIPSM quality assurance programs. The result is a uniform, chemically pure source of silicon dioxide and a stable alkali contribution for easier, more predictable batch formations. Consistently low levels of iron and other refractive elements offer the advantage of more uniform batch chemistry, for greater control without additions over critical quality parameters like viscosity, color and clarity.

Available throughout North America, GLASSIL consistency and uniformity is ideally suited to standardize incoming raw materials and to optimize batch economics in the production of flat and structural glass, container glass, tableware and decorative wares, fiberglass and silicates.

PARTICAL SIZE ANALYSIS

Typical Mean Values. These Do Not Represent A Specification.

	Mesh Size		GLASSIL® Grades	
	ASTM	MICRONS	520	540
Typical mean % retained on individual sieves	20	850	-	-
	30	600	0.1	0.1
	40	425	2.0	2.7
	50	300	18.6	31.6
	70	212	46.7	53.7
	100	150	23.1	11.1
	140	106	8.3	0.7
	200	75	1.1	0.1
	PAN	PAN	0.1	-

PHYSICAL PROPERTIES

Typical Mean Values. These Do Not Represent A Specification.

GLASSIL® Melting Sand		
Melting Point (°F/°C)	3135/1724	ASTM C-24
Specific Gravity (g/cm ³)	2.65	ASTM C-128
Moisture Content (%)	<0.1	ASTM C-566
Bulk Density/Aerated (lb/ft ³)	92-95	ASTM C-29
Bulk Density/Compacted (lb/ft ³)	98-100	ASTM C-29

CHEMICAL ANALYSIS

Typical Mean Values. These Do Not Represent A Specification.

	Typical Mean Percent by Weight	
	520	540
Silicon Dioxide (SiO ₂)	99.65	99.82
Iron Oxide (Fe ₂ O ₃)	0.08	0.06
Aluminum Oxide (Al ₂ O ₃)	0.14	0.07
Calcium Oxide (CaO)	0.01	0.01
Titanium Dioxide (TiO ₂)	0.04	0.03
Magnesium Oxide (MgO)	tr	tr
Potassium Oxide (K ₂ O)	0.04	0.01
Sodium Oxide (Na ₂ O)	0.01	tr
Loss on Ignition (LOI)	0.06	0.08

SHIPPING/ORDERING INFORMATION

- Shipping Point: Dividing Creek, NJ
- Originating Carrier: Winchester & Western Railroad
- Availability: Bulk Only
Truck and Rail

CUSTOMER SERVICE

US & Canada: 1-800-243-9004
 Fax: 1-800-243-9005
 Worldwide: 1-203-442-2500
 Fax: 1-203-972-1378

3 Summit Park Drive, Suite 700, Independence, OH 44131 | CoviaCorp.com

GRADE NUMBERS INDICATE RELATIVE VALUES OR RESULTS. THEY ARE NOT A SPECIFICATION OR WARRANTY OF PERFORMANCE.

Health Hazard Warnings: Prolonged inhalation of dust associated with the materials described in this data sheet can cause delayed lung injury including Silicosis, a progressive, disabling and sometimes fatal lung disease. IARC and NTP have determined that crystalline silica can cause lung cancer in humans. Risk of injury is dependent on the duration and level of exposure. Follow OSHA or other relevant safety and health standards for the form of crystalline silica called Quartz. Current safety data sheet, containing safety information, is available and should be consulted before usage.

Notice: While information contained herein is correct to the best of our knowledge, Covia hereby disclaims any warranties as to the accuracy of the same. Recommendations or suggestions are made without guarantee or representation as to result, since conditions of usage are beyond our control. All materials are sold subject to Covia's standard terms and conditions of sale and the condition that buyer shall make his own tests to determine the suitability of such product for buyer's purpose. No statement contained herein shall be construed as a license to operate under or as a recommendation to infringe any patent.

Silica/Silica Containing

COVIA and GLASSIL® are trademarks of Covia Holdings Corporations and/or its subsidiaries. All rights reserved.