

FEATURES & BENEFITS

CERASIL® Ceramic Grade Ground Silica is produced from high purity crystalline silica feedstock for the formulation and manufacture of ceramic whitewares, enamels and glazes.

When incorporated in ceramic bodies, CERASIL will reduce shrinkage during drying, increase the body's coefficient of thermal expansion, and help add plasticity to the finished product. CERASIL reacts during firing with other formula constituents to develop a lattice-like structure that strengthens the body while providing an exit for evolved gasses. In ceramic glazes and enamels, CERASIL will help regulate the melting point and control melt viscosity. The infusion of silica in the glaze will decrease its thermal expansion and, improve the glaze to body fit for greater craze resistance.

All CERASIL grades are processed with rigid adherence to Covia QIPsm quality assurance programs. Statistical control of grain distribution and the absence of "large" particles insure that CERASIL will be completely fused during vitrification. Chemical purity and consistency guarantee that CERASIL will fire white with predictable and repeatable results.

PARTICAL SIZE ANALYSIS

Typical Mean Values. These Do Not Represent A Specification.

	Mesh Size		CERASIL® Grade
	ASTM	MICRONS	200
Typical mean % retained on individual sieves	70	212	—
	100	150	—
	140	106	0.1
	200	75	1.4
	325	45	12.8
% Finer than	325	45	85.8
Median Particle Size (cm ² /g)			4000-4500

PHYSICAL PROPERTIES

Typical Mean Values. These Do Not Represent A Specification.

CERASIL® Ceramic Flint		
Specific Gravity (g/cm ³)	2.65	ASTM C-128
Moisture Content (%)	<0.1	ASTM C-566
Fusion Point (Pyrometric Cone)	32.5	ASTM C-24
Melting Point (°F/°C)	3135/1724	ASTM C-24
pH (%)	6.9-7.2	ASTM C-113-87-S
Bulk Density, loose (lb/ft ³)	65-70	ASTM C-29
Bulk Density, compacted (lb/ft ³)	85-90	ASTM C-29

CHEMICAL ANALYSIS

Typical Mean Values. These Do Not Represent A Specification.

Typical Mean Percent by Weight	
Silicon Dioxide (SiO ₂)	99.61
Iron Oxide (Fe ₂ O ₃)	0.03
Aluminum Oxide (Al ₂ O ₃)	0.21
Calcium Oxide (CaO)	0.01
Titanium Dioxide (TiO ₂)	0.01
Magnesium Oxide (MgO)	0.01
Potassium Oxide (K ₂ O)	0.01
Sodium Oxide (Na ₂ O)	tr
Loss on Ignition (LOI)	0.11

SHIPPING/ORDERING INFORMATION

- Shipping Point: Lugoff, SC
- Originating Carrier: CSX Railroad
- Availability: Bulk Only
Truck and Rail

CUSTOMER SERVICE

US & Canada: 1-800-243-9004

Fax: 1-800-243-9005

Worldwide: 1-203-442-2500

Fax: 1-203-972-1378

3 Summit Park Drive, Suite 700, Independence, OH 44131 | CoviaCorp.com

GRADE NUMBERS INDICATE RELATIVE VALUES OR RESULTS. THEY ARE NOT A SPECIFICATION OR WARRANTY OF PERFORMANCE.

HEALTH HAZARD WARNING: Prolonged inhalation of dust associated with the materials described in this data sheet can cause delayed lung injury including Silicosis, a progressive, disabling and sometimes fatal lung disease. IARC and NTP have determined that crystalline silica can cause lung cancer in humans. Risk of injury is dependent on the duration and level of exposure. Follow OSHA or other relevant safety and health standards for the form of crystalline silica called Quartz. Current safety data sheet, containing safety information, is available and should be consulted before usage.

Notice: While information contained herein is correct to the best of our knowledge, Covia hereby disclaims any warranties as to the accuracy of the same. Recommendations or suggestions are made without guarantee or representation as to result, since conditions of usage are beyond our control. All materials are sold subject to Covia's standard terms and conditions of sale and the condition that buyer shall make his own tests to determine the suitability of such product for buyer's purpose. No statement contained herein shall be construed as a recommendation to infringe any patent.

Silica/Silica Containing

COVIA and CERASIL® are trademarks of Covia Holdings Corporations and/or its subsidiaries. All rights reserved.