

FEATURES & BENEFITS

FILTERSIL® Filtration Sand and Gravel is produced from high-purity monocrystalline industrial quartz sand. FILTERSIL grades are engineered to perform in mixed media and pressure filters for portable water filtration and have been proven effective in industrial process water filtration and waste treatment. Resistant to degradation during handling and backwashing, these dense and durable sands effectively improve filter efficiency with optimized flow rates and reduced maintenance downtime.

In water producing wells, FILTERSIL will increase the yield from the aquifer by increasing the permeable zone around the well screen. FILTERSIL's ability to effectively bridge and filter finer or highly laminated formation at the interface offer drillers the option to use larger slot sizes for improved hydraulic conductivity with little or no headloss through the filter pack.

All FILTERSIL grades are processed and sized with strict adherence to Covia's QIPSM statistical and quality assurance controls. FILTERSIL meets all AWWA B-100, ANSI, and NSF-61 standards for consistently uniform and chemically inert filter media.

PARTICAL SIZE ANALYSIS

Typical mean values. These do not represent a specification.

	Mesh Size		FILTERSIL® Grades					
	ASTM	MICRONS	1.25	0.65	0.50	0.35	0.15	0.10
Typical mean % retained on individual sieves	8	2.36 mm	0.9	–	–	–	–	–
	16	1.18 mm	92.5	42.7	0.1	–	–	–
	20	850	5.4	49.2	24.7	–	–	–
	30	600	0.9	6.8	57.7	24.3	0.2	–
	40	425	0.2	1.2	15.7	62.9	12.4	0.5
	50	300	0.1	0.1	1.7	12.5	34.6	4.2
	70	212	tr	tr	0.1	0.2	27.1	30.0
	100	150	tr	–	–	0.1	17.3	39.0
	140	100	–	–	–	–	6.5	17.6
	200	75	–	–	–	–	1.6	6.3
	PAN	PAN	–	–	–	–	0.3	2.4
Effective Size (mm)	–		1.22	0.86	0.52	0.40	0.16	0.11
Uniformity Coefficient	–		1.52	1.5	1.6	1.4	2.09	1.86
Approximate Screen Slot (inches)	–		0.030	0.020	0.015	N/A	N/A	N/A

PHYSICAL PROPERTIES

Typical mean values. These do not represent a specification.

FILTERSIL® Filtration Sand and Gravel		
Grain Shape	Subangular	Visual
Hardness (Mohs)	7.0	Moh's Scale
pH	6.0-8.0	AFS 113-87-S
Acid Solubility (%)	<0.5	API RP56
Moisture Content (%)	<0.1	ASTM C-566
Specific Gravity (g/cm3)	2.65	ASTM C-128
Bulk Density, loose (lb/ft3)	92-95	ASTM C-29
Bulk Density, compacted (lb/ft3)	98-100	ASTM C-29



This product is certified by NSF to NSF/ANSI Standard 61

CHEMICAL ANALYSIS

Typical mean values. These do not represent a specification.

	Typical Mean Percent by Weight		
	1.25-0.65	0.50-0.35	1.15-0.10
Silicon Dioxide (SiO ₂)	89.59	87.53	85.27
Iron Oxide (Fe ₂ O ₃)	0.12	0.11	0.16
Aluminum Oxide (Al ₂ O ₃)	6.38	7.09	8.47
Calcium Oxide (CaO)	0.32	0.45	0.70
Titanium Dioxide (TiO ₂)	0.02	0.02	0.05
Magnesium Oxide (MgO)	0.03	0.03	0.03
Potassium Oxide (K ₂ O)	3.20	3.25	3.22
Sodium Oxide (Na ₂ O)	1.10	1.38	1.92
Loss on Ignition (LOI)	0.14	0.15	0.18

SHIPPING/ORDERING INFORMATION

- Shipping Point: Emmett, ID
- Originating Carrier: Union Pacific
- Availability: Bulk, 3000# IBC and 50 lb Paper Bag
Truck and Rail

CUSTOMER SERVICE

US & Canada: 1-800-243-9004

Fax: 1-800-243-9005

Worldwide: 1-203-442-2500

Fax: 1-203-972-1378

3 Summit Park Drive, Suite 700, Independence, OH 44131 | CoviaCorp.com

GRADE NUMBERS INDICATE RELATIVE VALUES OR RESULTS. THEY ARE NOT A SPECIFICATION OR WARRANTY OF PERFORMANCE.

HEALTH HAZARD WARNING: Prolonged inhalation of dust associated with the materials described in this data sheet can cause delayed lung injury including Silicosis, a progressive, disabling and sometimes fatal lung disease. IARC and NTP have determined that crystalline silica can cause lung cancer in humans. Risk of injury is dependent on the duration and level of exposure. Follow OSHA or other relevant safety and health standards for the form of crystalline silica called Quartz. Current safety data sheet, containing safety information, is available and should be consulted before usage.

Notice: While information contained herein is correct to the best of our knowledge, Covia hereby disclaims any warranties as to the accuracy of the same. Recommendations or suggestions are made without guarantee or representation as to result, since conditions of usage are beyond our control. All materials are sold subject to Covia's standard terms and conditions of sale and the condition that buyer shall make his own tests to determine the suitability of such product for buyer's purpose. No statement contained herein shall be construed as a license to operate under or as a recommendation to infringe any patent.

Silica/Silica Containing

COVIA and FILTERSIL® are trademarks of Covia Holdings Corporation and/or its subsidiaries. All rights reserved.